



1 Identification

- **Product identifier**
- **Trade name:** Steelkote 825 Fast Dry High Solids Epoxy Primer Light Gray
- **Article number:** 825B060
- **Details of the supplier of the safety data sheet**
- **Manufacturer/Supplier:**
 Baril Coatings USA, LLC
 401 Growth Parkway
 Angola, IN 46703
- **Information department:** Product safety department
- **Emergency telephone number:** During normal opening times: +1 (260) 665-8431

2 Hazard(s) identification

- **Classification of the substance or mixture**



GHS02 Flame

Flam. Liq. 3 H226 Flammable liquid and vapor.



GHS08 Health hazard

Muta. 1B H340 May cause genetic defects.

Carc. 1A H350 May cause cancer.



GHS07

Skin Irrit. 2 H315 Causes skin irritation.

Eye Irrit. 2A H319 Causes serious eye irritation.

Skin Sens. 1 H317 May cause an allergic skin reaction.

- **Label elements**

- **GHS label elements**

The product is classified and labeled according to the Globally Harmonized System (GHS).

- **Hazard pictograms**



GHS02



GHS07



GHS08

Trade name: Steelkote 825 Fast Dry High Solids Epoxy Primer Light Gray

(Contd. of page 1)

· **Signal word** *Danger*· **Hazard-determining components of labeling:**Quartz (SiO₂)reaction product: bisphenol-A-(epichlorhydrin) epoxy resin (number average molecular weight ≤ 700)

Solvent naphtha (petroleum), light arom.

titanium dioxide

oxirane, mono[(C12-14-alkyloxy)methyl] derivs

· **Hazard statements***Flammable liquid and vapor.**Causes skin irritation.**Causes serious eye irritation.**May cause an allergic skin reaction.**May cause genetic defects.**May cause cancer.*· **Precautionary statements***If medical advice is needed, have product container or label at hand.**Keep out of reach of children.**Read label before use.**Obtain special instructions before use.**Do not handle until all safety precautions have been read and understood.**Keep away from heat/sparks/open flames/hot surfaces. - No smoking.**Keep container tightly closed.**Ground/bond container and receiving equipment.**Use explosion-proof electrical/ventilating/lighting/equipment.**Use only non-sparking tools.**Take precautionary measures against static discharge.**Avoid breathing dust/fume/gas/mist/vapors/spray**Wash thoroughly after handling.**Contaminated work clothing must not be allowed out of the workplace.**Wear protective gloves/protective clothing/eye protection/face protection.**If on skin (or hair): Take off immediately all contaminated clothing. Rinse skin with water/shower.**If in eyes: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.**IF exposed or concerned: Get medical advice/attention.**Specific treatment (see on this label).**Take off contaminated clothing and wash it before reuse.**If skin irritation or rash occurs: Get medical advice/attention.**If eye irritation persists: Get medical advice/attention.**Wash contaminated clothing before reuse.**In case of fire: Use for extinction: CO₂, powder or water spray.**Store in a well-ventilated place. Keep cool.**Store locked up.**Dispose of contents/container in accordance with local/regional/national/international regulations.*· **Classification system:**· **NFPA ratings (scale 0 - 4)**

Health = 1

Fire = 3

Reactivity = 0

· **HMIS-ratings (scale 0 - 4)**

Health = *2

Fire = 3

Reactivity = 0

(Contd. on page 3)

Trade name: **Steelkote 825 Fast Dry High Solids Epoxy Primer Light Gray**

(Contd. of page 2)

- **Other hazards**
- **Results of PBT and vPvB assessment**
- **PBT:** Not applicable.
- **vPvB:** Not applicable.

3 Composition/information on ingredients

- **Chemical characterization: Mixtures**
- **Description:** Mixture of the substances listed below with nonhazardous additions.

- **Dangerous components:**

1330-20-7	xylene	>10-≤25%
13463-67-7	titanium dioxide	>10-≤25%
7727-43-7	barium sulphate, natural	>10-≤25%
14808-60-7	Quartz (SiO ₂)	>2.5-≤10%
110-43-0	Methyl n-amyl ketone	>2.5-≤10%
25068-38-6	reaction product: bisphenol-A-(epichlorhydrin) epoxy resin (number average molecular weight ≤ 700)	≥5-≤10%
68609-97-2	oxirane, mono[(C12-14-alkyloxy)methyl] derivs	>2.5-<10%
78-93-3	butanone	≤2.5%
108-10-1	4-methylpentan-2-one	≥0.1-≤2.5%
100-41-4	ethylbenzene	≥0.1-≤2.5%
64742-95-6	Solvent naphtha (petroleum), light arom.	≥0.1-≤2.5%
1333-86-4	Carbon black	≥0.1-≤2.5%

4 First-aid measures

- **Description of first aid measures**
- **General information:**
Symptoms of poisoning may even occur after several hours; therefore medical observation for at least 48 hours after the accident.
- **After inhalation:**
Supply fresh air and to be sure call for a doctor.
In case of unconsciousness place patient stably in side position for transportation.
- **After skin contact:** Immediately wash with water and soap and rinse thoroughly.
- **After eye contact:**
Rinse opened eye for several minutes under running water. If symptoms persist, consult a doctor.
- **After swallowing:** If symptoms persist consult doctor.
- **Information for doctor:**
- **Most important symptoms and effects, both acute and delayed**
No further relevant information available.
- **Indication of any immediate medical attention and special treatment needed**
No further relevant information available.

5 Fire-fighting measures

- **Extinguishing media**
- **Suitable extinguishing agents:**
CO₂, extinguishing powder or water spray. Fight larger fires with water spray or alcohol resistant foam.
- **For safety reasons unsuitable extinguishing agents:** Water with full jet

(Contd. on page 4)

Trade name: Steelkote 825 Fast Dry High Solids Epoxy Primer Light Gray

(Contd. of page 3)

- **Special hazards arising from the substance or mixture** No further relevant information available.
- **Advice for firefighters**
- **Protective equipment:** Mouth respiratory protective device.

6 Accidental release measures

- **Personal precautions, protective equipment and emergency procedures**
Wear protective equipment. Keep unprotected persons away.
- **Environmental precautions:**
Do not allow product to reach sewage system or any water course.
Inform respective authorities in case of seepage into water course or sewage system.
Do not allow to enter sewers/ surface or ground water.
- **Methods and material for containment and cleaning up:**
Absorb with liquid-binding material (sand, diatomite, acid binders, universal binders, sawdust).
Dispose contaminated material as waste according to item 13.
Ensure adequate ventilation.
Do not flush with water or aqueous cleansing agents
- **Reference to other sections**
See Section 7 for information on safe handling.
See Section 8 for information on personal protection equipment.
See Section 13 for disposal information.
- **Protective Action Criteria for Chemicals**

· PAC-1:

25036-25-3	Diglycidyl ether of bisphenol A	12 mg/m ³
1330-20-7	xylene	130 ppm
13463-67-7	titanium dioxide	30 mg/m ³
7727-43-7	barium sulphate, natural	15 mg/m ³
14808-60-7	Quartz (SiO ₂)	0.075 mg/m ³
110-43-0	Methyl n-amyl ketone	150 ppm
7779-90-0	trizinc bis(orthophosphate)	12 mg/m ³
25068-38-6	reaction product: bisphenol-A-(epichlorhydrin) epoxy resin (number average molecular weight ≤ 700)	90 mg/m ³
1314-13-2	zinc oxide	10 mg/m ³
78-93-3	butanone	200 ppm
108-10-1	4-methylpentan-2-one	75 ppm
1344-28-1	aluminium oxide	15 mg/m ³
78-92-2	butanol	150 ppm
2530-83-8	[3-(2,3-epoxypropoxy)propyl]trimethoxysilane	9.3 mg/m ³
100-41-4	ethylbenzene	33 ppm
1314-23-4	zirconium dioxide	14 mg/m ³
108-38-3	m-xylene	130 ppm
108-65-6	2-methoxy-1-methylethyl acetate	50 ppm
7631-86-9	silicon dioxide, chemically prepared	18 mg/m ³
1333-86-4	Carbon black	9 mg/m ³

· PAC-2:

25036-25-3	Diglycidyl ether of bisphenol A	130 mg/m ³
1330-20-7	xylene	920* ppm
13463-67-7	titanium dioxide	330 mg/m ³

(Contd. on page 5)

Trade name: Steelkote 825 Fast Dry High Solids Epoxy Primer Light Gray

(Contd. of page 4)

7727-43-7	barium sulphate, natural	170 mg/m ³
14808-60-7	Quartz (SiO ₂)	33 mg/m ³
110-43-0	Methyl n-amyl ketone	670 ppm
7779-90-0	trizinc bis(orthophosphate)	36 mg/m ³
25068-38-6	reaction product: bisphenol-A-(epichlorhydrin) epoxy resin (number average molecular weight ≤ 700)	990 mg/m ³
1314-13-2	zinc oxide	15 mg/m ³
78-93-3	butanone	2700* ppm
108-10-1	4-methylpentan-2-one	500 ppm
1344-28-1	aluminium oxide	170 mg/m ³
78-92-2	butanol	220 ppm
2530-83-8	[3-(2,3-epoxypropoxy)propyl]trimethoxysilane	100 mg/m ³
100-41-4	ethylbenzene	1100* ppm
1314-23-4	zirconium dioxide	110 mg/m ³
108-38-3	m-xylene	920 ppm
108-65-6	2-methoxy-1-methylethyl acetate	1,000 ppm
7631-86-9	silicon dioxide, chemically prepared	740 mg/m ³
1333-86-4	Carbon black	99 mg/m ³

PAC-3:

25036-25-3	Diglycidyl ether of bisphenol A	790 mg/m ³
1330-20-7	xylene	2500* ppm
13463-67-7	titanium dioxide	2,000 mg/m ³
7727-43-7	barium sulphate, natural	990 mg/m ³
14808-60-7	Quartz (SiO ₂)	200 mg/m ³
110-43-0	Methyl n-amyl ketone	4000* ppm
7779-90-0	trizinc bis(orthophosphate)	220 mg/m ³
25068-38-6	reaction product: bisphenol-A-(epichlorhydrin) epoxy resin (number average molecular weight ≤ 700)	5,900 mg/m ³
1314-13-2	zinc oxide	2,500 mg/m ³
78-93-3	butanone	4000* ppm
108-10-1	4-methylpentan-2-one	3000* ppm
1344-28-1	aluminium oxide	990 mg/m ³
78-92-2	butanol	10000** ppm
2530-83-8	[3-(2,3-epoxypropoxy)propyl]trimethoxysilane	230 mg/m ³
100-41-4	ethylbenzene	1800* ppm
1314-23-4	zirconium dioxide	680 mg/m ³
108-38-3	m-xylene	2500* ppm
108-65-6	2-methoxy-1-methylethyl acetate	5000* ppm
7631-86-9	silicon dioxide, chemically prepared	4,500 mg/m ³
1333-86-4	Carbon black	590 mg/m ³

US

(Contd. on page 6)

Trade name: Steelkote 825 Fast Dry High Solids Epoxy Primer Light Gray

(Contd. of page 5)

7 Handling and storage

- **Handling:**
- **Precautions for safe handling**
Ensure good ventilation/exhaustion at the workplace.
Open and handle receptacle with care.
Prevent formation of aerosols.
- **Information about protection against explosions and fires:**
Keep ignition sources away - Do not smoke.
Protect against electrostatic charges.
Keep respiratory protective device available.
- **Conditions for safe storage, including any incompatibilities**
- **Storage:**
- **Requirements to be met by storerooms and receptacles:** No special requirements.
- **Information about storage in one common storage facility:** Not required.
- **Further information about storage conditions:** Keep receptacle tightly sealed.
- **Specific end use(s)** No further relevant information available.

8 Exposure controls/personal protection

- **Additional information about design of technical systems:** No further data; see item 7.
- **Control parameters**
- **Components with limit values that require monitoring at the workplace:**
The following constituents are the only constituents of the product which have a PEL, TLV or other recommended exposure limit.
At this time, the other constituents have no known exposure limits.

1330-20-7 xylene	
PEL	Long-term value: 435 mg/m ³ , 100 ppm
REL	Short-term value: 655 mg/m ³ , 150 ppm Long-term value: 435 mg/m ³ , 100 ppm
TLV	Short-term value: 651 mg/m ³ , 150 ppm Long-term value: 434 mg/m ³ , 100 ppm BEI
7727-43-7 barium sulphate, natural	
PEL	Long-term value: 15* 5** mg/m ³ *total dust **respirable fraction
REL	Long-term value: 10* 5** mg/m ³ *total dust **respirable fraction
TLV	Long-term value: 5* mg/m ³ *inhalable fraction; E
14808-60-7 Quartz (SiO₂)	
PEL	Long-term value: 0.05* mg/m ³ *resp. dust; 30mg/m ³ /%SiO ₂ +2
REL	Long-term value: 0.05* mg/m ³ *respirable dust; See Pocket Guide App. A
TLV	Long-term value: 0.025* mg/m ³ *as respirable fraction
110-43-0 Methyl n-amyl ketone	
PEL	Long-term value: 465 mg/m ³ , 100 ppm

(Contd. on page 7)

Trade name: Steelkote 825 Fast Dry High Solids Epoxy Primer Light Gray

(Contd. of page 6)

REL Long-term value: 465 mg/m³, 100 ppmTLV Long-term value: 233 mg/m³, 50 ppm**78-93-3 butanone**PEL Long-term value: 590 mg/m³, 200 ppmREL Short-term value: 885 mg/m³, 300 ppmLong-term value: 590 mg/m³, 200 ppmTLV Short-term value: 885 mg/m³, 300 ppmLong-term value: 590 mg/m³, 200 ppm

BEI

108-10-1 4-methylpentan-2-onePEL Long-term value: 410 mg/m³, 100 ppmREL Short-term value: 300 mg/m³, 75 ppmLong-term value: 205 mg/m³, 50 ppmTLV Short-term value: 307 mg/m³, 75 ppmLong-term value: 82 mg/m³, 20 ppm

BEI

100-41-4 ethylbenzenePEL Long-term value: 435 mg/m³, 100 ppmREL Short-term value: 545 mg/m³, 125 ppmLong-term value: 435 mg/m³, 100 ppmTLV Long-term value: 87 mg/m³, 20 ppm

BEI

1333-86-4 Carbon blackPEL Long-term value: 3.5 mg/m³REL Long-term value: 3.5* mg/m³

*0.1 in presence of PAHs; See Pocket Guide Apps.A+C

TLV Long-term value: 3* mg/m³

*inhalable fraction

Ingredients with biological limit values:**1330-20-7 xylene**

BEI 1.5 g/g creatinine

Medium: urine

Time: end of shift

Parameter: Methylhippuric acids

78-93-3 butanone

BEI 2 mg/L

Medium: urine

Time: end of shift

Parameter: MEK

108-10-1 4-methylpentan-2-one

BEI 1 mg/L

Medium: urine

Time: end of shift

Parameter: MIBK

(Contd. on page 8)

Trade name: **Steelkote 825 Fast Dry High Solids Epoxy Primer Light Gray**

(Contd. of page 7)

100-41-4 ethylbenzene

BEI	0.7 g/g creatinine
	Medium: urine
	Time: end of shift at end of workweek
	Parameter: Sum of mandelic acid and phenylglyoxylic acid (nonspecific, semi-quantitative)
	-
	Medium: end-exhaled air
	Time: not critical
	Parameter: Ethyl benzene (semi-quantitative)

· **Additional information:** The lists that were valid during the creation were used as basis.

· **Exposure controls**

· **Personal protective equipment:**

· **General protective and hygienic measures:**

Keep away from foodstuffs, beverages and feed.
Immediately remove all soiled and contaminated clothing.
Wash hands before breaks and at the end of work.
Store protective clothing separately.
Avoid contact with the eyes and skin.

· **Breathing equipment:**

In case of brief exposure or low pollution use respiratory filter device. In case of intensive or longer exposure use respiratory protective device that is independent of circulating air.

· **Protection of hands:**



Protective gloves

The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/ the chemical mixture.

Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation

· **Material of gloves**

The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application.

· **Penetration time of glove material**

The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed.

· **Eye protection:**



Tightly sealed goggles

US

(Contd. on page 9)

Trade name: Steelkote 825 Fast Dry High Solids Epoxy Primer Light Gray

(Contd. of page 8)

9 Physical and chemical properties· **Information on basic physical and chemical properties**· **General Information**· **Appearance:****Form:**

Liquid

Color:

Grey

· **Odor:**

Solvent-like

· **Odor threshold:**

Not determined.

· **pH-value:**

Not determined.

· **Change in condition****Melting point/Melting range:**

Undetermined.

Boiling point/Boiling range:

137-143 °C (278.6-289.4 °F)

· **Flash point:**

23 - 60 °C (73.4-140 °F)

· **Flammability (solid, gaseous):**

Not applicable.

· **Ignition temperature:**

500 °C (932 °F)

· **Decomposition temperature:**

Not determined.

· **Auto igniting:**

Product is not selfigniting.

· **Danger of explosion:**

Product is not explosive. However, formation of explosive air/vapor mixtures are possible.

· **Explosion limits:****Lower:**

1.1 Vol %

Upper:

7 Vol %

· **Vapor pressure at 20 °C (68 °F):**

6.7-8.2 hPa (5-6.2 mm Hg)

· **Density at 20 °C (68 °F):**1.51 g/cm³ (12.6 lbs/gal)· **Relative density**

Not determined.

· **Vapor density**

Not determined.

· **Evaporation rate**

Not determined.

· **Solubility in / Miscibility with****Water:**

Miscible

· **Partition coefficient (n-octanol/water):** Not determined.· **Viscosity:****Dynamic:**

Not determined.

Kinematic:

Not determined.

· **Solvent content:****Organic solvents:**

23.8 %

VOC content:

23.81 %

359.5 g/l / 3.00 lb/gal

Solids content:

75.7 % (by weight)

· **Other information:**

No further relevant information available.

10 Stability and reactivity· **Reactivity** No further relevant information available.

(Contd. on page 10)

Trade name: Steelkote 825 Fast Dry High Solids Epoxy Primer Light Gray

(Contd. of page 9)

- **Chemical stability**
- **Thermal decomposition / conditions to be avoided:**
No decomposition if used according to specifications.
- **Possibility of hazardous reactions** No dangerous reactions known.
- **Conditions to avoid** No further relevant information available.
- **Incompatible materials:** No further relevant information available.
- **Hazardous decomposition products:** No dangerous decomposition products known.

11 Toxicological information

- **Information on toxicological effects**
- **Acute toxicity:**

- **LD/LC50 values that are relevant for classification:**

1330-20-7 xylene		
Oral	LD50	4,300 mg/kg (rat)
Dermal	LD50	2,000 mg/kg (rabbit)
7779-90-0 trizinc bis(orthophosphate)		
Oral	LD50	>5,000 mg/kg (rat)
1314-13-2 zinc oxide		
Oral	LD50	>5,000 mg/kg (rat)
64742-95-6 Solvent naphtha (petroleum), light arom.		
Oral	LD50	>6,800 mg/kg (rat)
Dermal	LD50	>3,400 mg/kg (rab)
Inhalative	LC50/4 h	>10.2 mg/l (rat)

- **Primary irritant effect:**
- **on the skin:** Irritant to skin and mucous membranes.
- **on the eye:** Irritating effect.
- **Sensitization:** Sensitization possible through skin contact.
- **Additional toxicological information:**
The product shows the following dangers according to internally approved calculation methods for preparations:
Harmful
Irritant
Carcinogenic.
The product can cause inheritable damage.

- **Carcinogenic categories**

IARC (International Agency for Research on Cancer)		
1330-20-7	xylene	3
13463-67-7	titanium dioxide	2B
14808-60-7	Quartz (SiO ₂)	1
14807-96-6	Talc (Mg ₃ H ₂ (SiO ₃) ₄)	3
108-10-1	4-methylpentan-2-one	2B
100-41-4	ethylbenzene	2B
108-38-3	m-xylene	3
106-42-3	p-xylene	3
95-47-6	o-xylene	3
7631-86-9	silicon dioxide, chemically prepared	3

(Contd. on page 11)

Trade name: Steelkote 825 Fast Dry High Solids Epoxy Primer Light Gray

(Contd. of page 10)

1333-86-4	Carbon black	2B
· NTP (National Toxicology Program)		
14808-60-7	Quartz (SiO ₂)	K
· OSHA-Ca (Occupational Safety & Health Administration)		
None of the ingredients is listed.		

12 Ecological information

- **Toxicity**
- **Aquatic toxicity:** No further relevant information available.
- **Persistence and degradability** No further relevant information available.
- **Behavior in environmental systems:**
- **Bioaccumulative potential** No further relevant information available.
- **Mobility in soil** No further relevant information available.
- **Ecotoxicological effects:**
- **Remark:** Toxic for fish
- **Additional ecological information:**
- **General notes:**
Water hazard class 3 (Self-assessment): extremely hazardous for water
Do not allow product to reach ground water, water course or sewage system, even in small quantities.
Danger to drinking water if even extremely small quantities leak into the ground.
Also poisonous for fish and plankton in water bodies.
Toxic for aquatic organisms
- **Results of PBT and vPvB assessment**
- **PBT:** Not applicable.
- **vPvB:** Not applicable.
- **Other adverse effects** No further relevant information available.

13 Disposal considerations

- **Waste treatment methods**
- **Recommendation:**
Must not be disposed of together with household garbage. Do not allow product to reach sewage system.
- **Uncleaned packagings:**
- **Recommendation:** Disposal must be made according to official regulations.

14 Transport information

· UN-Number	UN1263
· DOT, IMDG, IATA	
· UN proper shipping name	Paint
· DOT	PAINT (trizinc bis(orthophosphate), reaction product: bisphenol-A-(epichlorhydrin) epoxy resin (number average molecular weight ≤ 700)), MARINE POLLUTANT
· IMDG	PAINT
· IATA	

(Contd. on page 12)

Trade name: Steelkote 825 Fast Dry High Solids Epoxy Primer Light Gray

(Contd. of page 11)

· **Transport hazard class(es)**· **DOT**· **Class**

3 Flammable liquids

· **Label**

3

· **IMDG**· **Class**

3 Flammable liquids

· **Label**

3

· **IATA**· **Class**

3 Flammable liquids

· **Label**

3

· **Packing group**· **DOT, IMDG, IATA**

III

· **Environmental hazards:**

Product contains environmentally hazardous substances:
reaction product: bisphenol-A-(epichlorhydrin) epoxy
resin (number average molecular weight ≤ 700)

· **Marine pollutant:**

Symbol (fish and tree)

· **Special precautions for user**

Warning: Flammable liquids

· **Danger code (Kemler):**

30

· **EMS Number:**

F-E, S-E

· **Stowage Category**

A

· **Transport in bulk according to Annex II of
MARPOL73/78 and the IBC Code**

Not applicable.

· **Transport/Additional information:**· **DOT**· **Quantity limitations**

On passenger aircraft/rail: 60 L

On cargo aircraft only: 220 L

· **IMDG**· **Limited quantities (LQ)**

5L

· **Excepted quantities (EQ)**

Code: E1

Maximum net quantity per inner packaging: 30 ml

Maximum net quantity per outer packaging: 1000 ml

(Contd. on page 13)

Trade name: Steelkote 825 Fast Dry High Solids Epoxy Primer Light Gray

(Contd. of page 12)

· **UN "Model Regulation":** UN 1263 PAINT, 3, III, ENVIRONMENTALLY HAZARDOUS

15 Regulatory information

· **Safety, health and environmental regulations/legislation specific for the substance or mixture**
· **Sara**

· **Section 355 (extremely hazardous substances):**

None of the ingredients is listed.

· **Section 313 (Specific toxic chemical listings):**

1330-20-7	xylene
7727-43-7	barium sulphate, natural
7779-90-0	trizinc bis(orthophosphate)
1314-13-2	zinc oxide
108-10-1	4-methylpentan-2-one
1344-28-1	aluminium oxide
78-92-2	butanol
100-41-4	ethylbenzene
108-38-3	m-xylene
106-42-3	p-xylene
95-47-6	o-xylene

· **TSCA (Toxic Substances Control Act):**

All ingredients are listed.

· **Proposition 65**

· **Chemicals known to cause cancer:**

13463-67-7	titanium dioxide
14808-60-7	Quartz (SiO ₂)
108-10-1	4-methylpentan-2-one
100-41-4	ethylbenzene
1333-86-4	Carbon black

· **Chemicals known to cause reproductive toxicity for females:**

None of the ingredients is listed.

· **Chemicals known to cause reproductive toxicity for males:**

None of the ingredients is listed.

· **Chemicals known to cause developmental toxicity:**

108-10-1	4-methylpentan-2-one
----------	----------------------

· **Carcinogenic categories**

· **EPA (Environmental Protection Agency)**

1330-20-7	xylene	I
7727-43-7	barium sulphate, natural	D, CBD(inh), NL(oral)
7779-90-0	trizinc bis(orthophosphate)	D, I, II
1314-13-2	zinc oxide	D, I, II
78-93-3	butanone	I

(Contd. on page 14)

Trade name: Steelkote 825 Fast Dry High Solids Epoxy Primer Light Gray

(Contd. of page 13)

108-10-1	4-methylpentan-2-one	I
100-41-4	ethylbenzene	D
108-38-3	m-xylene	I
106-42-3	p-xylene	I
95-47-6	o-xylene	I

· **TLV (Threshold Limit Value established by ACGIH)**

1330-20-7	xylene	A4
13463-67-7	titanium dioxide	A4
14808-60-7	Quartz (SiO ₂)	A2
14807-96-6	Talc (Mg ₃ H ₂ (SiO ₃) ₄)	A4
1344-28-1	aluminium oxide	A4
100-41-4	ethylbenzene	A3
1314-23-4	zirconium dioxide	A4
108-38-3	m-xylene	A4
106-42-3	p-xylene	A4
95-47-6	o-xylene	A4
1333-86-4	Carbon black	A4

· **NIOSH-Ca (National Institute for Occupational Safety and Health)**

13463-67-7	titanium dioxide
14808-60-7	Quartz (SiO ₂)
1333-86-4	Carbon black

· **GHS label elements**

The product is classified and labeled according to the Globally Harmonized System (GHS).

· **Hazard pictograms**

GHS02 GHS07 GHS08

· **Signal word Danger**· **Hazard-determining components of labeling:**

Quartz (SiO₂)

reaction product: bisphenol-A-(epichlorhydrin) epoxy resin (number average molecular weight ≤ 700)

Solvent naphtha (petroleum), light arom.

titanium dioxide

oxirane, mono[(C12-14-alkyloxy)methyl] derivs

· **Hazard statements**

Flammable liquid and vapor.

Causes skin irritation.

Causes serious eye irritation.

May cause an allergic skin reaction.

May cause genetic defects.

May cause cancer.

· **Precautionary statements**

If medical advice is needed, have product container or label at hand.

Keep out of reach of children.

Read label before use.

Obtain special instructions before use.

Do not handle until all safety precautions have been read and understood.

(Contd. on page 15)

Trade name: Steelkote 825 Fast Dry High Solids Epoxy Primer Light Gray

(Contd. of page 14)

Keep away from heat/sparks/open flames/hot surfaces. - No smoking.
 Keep container tightly closed.
 Ground/bond container and receiving equipment.
 Use explosion-proof electrical/ventilating/lighting/equipment.
 Use only non-sparking tools.
 Take precautionary measures against static discharge.
 Avoid breathing dust/fume/gas/mist/vapors/spray
 Wash thoroughly after handling.
 Contaminated work clothing must not be allowed out of the workplace.
 Wear protective gloves/protective clothing/eye protection/face protection.
 If on skin (or hair): Take off immediately all contaminated clothing. Rinse skin with water/shower.
 If in eyes: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.
 IF exposed or concerned: Get medical advice/attention.
 Specific treatment (see on this label).
 Take off contaminated clothing and wash it before reuse.
 If skin irritation or rash occurs: Get medical advice/attention.
 If eye irritation persists: Get medical advice/attention.
 Wash contaminated clothing before reuse.
 In case of fire: Use for extinction: CO₂, powder or water spray.
 Store in a well-ventilated place. Keep cool.
 Store locked up.
 Dispose of contents/container in accordance with local/regional/national/international regulations.

- **National regulations:**

- **Information about limitation of use:**

Workers are not allowed to be exposed to the hazardous carcinogenic materials contained in this preparation. Exceptions can be made by the authorities in certain cases.

- **Chemical safety assessment:** A Chemical Safety Assessment has not been carried out.

16 Other information

This information is based on our present knowledge. However, this shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship.

- **Department issuing SDS:** Environment protection department.

- **Contact:** Mr. Williams

- **Date of preparation / last revision** 03/07/2024 / -

- **Abbreviations and acronyms:**

IMDG: International Maritime Code for Dangerous Goods

DOT: US Department of Transportation

IATA: International Air Transport Association

ACGIH: American Conference of Governmental Industrial Hygienists

EINECS: European Inventory of Existing Commercial Chemical Substances

ELINCS: European List of Notified Chemical Substances

CAS: Chemical Abstracts Service (division of the American Chemical Society)

NFPA: National Fire Protection Association (USA)

HMIS: Hazardous Materials Identification System (USA)

VOC: Volatile Organic Compounds (USA, EU)

LC50: Lethal concentration, 50 percent

LD50: Lethal dose, 50 percent

PBT: Persistent, Bioaccumulative and Toxic

vPvB: very Persistent and very Bioaccumulative

NIOSH: National Institute for Occupational Safety

OSHA: Occupational Safety & Health

TLV: Threshold Limit Value

PEL: Permissible Exposure Limit

REL: Recommended Exposure Limit

BEI: Biological Exposure Limit

Flam. Liq. 3: Flammable liquids – Category 3

(Contd. on page 16)

Printing date 03/07/2024

Reviewed on 01/30/2024

Trade name: Steelkote 825 Fast Dry High Solids Epoxy Primer Light Gray

(Contd. of page 15)

Skin Irrit. 2: Skin corrosion/irritation – Category 2
Eye Irrit. 2A: Serious eye damage/eye irritation – Category 2A
Skin Sens. 1: Skin sensitisation – Category 1
Muta. 1B: Germ cell mutagenicity – Category 1B
Carc. 1A: Carcinogenicity – Category 1A

— US —